# **Technical data sheet**



# **Bauder LiquiPAVE R**

### Product description

Application fields

LiquiPAVE R is a fast curing, cold applied liquid waterproofing resin. It is the resin component of LiquiPAVE RF Deck Floor Layer (see separate Technical Data Sheet). The product is a PMMA based resin and requires the addition of catalyst to cure. It is solvent, isocyanate and halogen free. LiquiPAVE R is used in the LiquiPAVE RF Deck Floor Layer in Bauder

LiquiTEC Balcony Systems. It is also used in conjunction with 110g Reinforcement Fleece for overbanding of dynamic cracks and joints in the substrate prior to installing the Deck Floor Layer.

The product must be mixed with Bauder Catalyst to cure. Bauder Catalyst must be ordered separately.



V5 26.10.2023

Article Number

GB81002010

Characteristic		Unit	Value			
Gross weight		kg	11.1			
Net weight		kg	10			
Colour			Transparent			
Base			Poly methyl methacrylate			
Coverage		kg/m²	Refer to LiquiPAVE RF Technical Data Sheet			
Coverage		kg/m²	2.5 kg/m <sup>2</sup> when used with Bauder 110g Reinforcement Fleece to overband cracks – refer to Bauder specification.			
Shelf life unopened		months	6			
Ambient and substrate temperature		°C	0 to +35 (Where the temperature falls outside of this, please refer to Summer & Winter advice documents from Bauder).			
Atmospheric relative humidity		%	≤ 95			
Dew point		°C	3° above dew point			
Pot life		minutes	15 approx.			
Curing time at 20°C* Rainproof Overcoat / traffic time Able to withstand stress		minutes	30 approx. 60 approx. 120 approx.			
*Times will be slightly increased at lower te	emperatures a	and slightly reduced at	higher temperatures.			
Storage guidance		Store unopened in a cool, dry, well-ventilated place above freezing, out of direct sunlight and in the original container.				
Packaging material	The pr	The product is packaged in tin plate steel pails with a tin plate steel lid and ring latch.				
	Weigh	Weight of packaging approximately 1.1kg.				
Handling/PPE	heavy	All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using the product, installers should be provided with, and wear, suitable personal protective equipment.				
Emptying and disposal guidance	e Containers which have been emptied, but not washed out in line with the specific methods and calculations prescribed in WP1 and WM3, should be classified as packaging containing residues of/or contaminated by hazardous substances using waste code 15-01-10. Containers with hazardous residues that have been emptied and washed-out in line with the method and calculations which are detailed in the industry guidance can be classified as non-hazardous waste packaging. Dependent upon the state of the waste resin, hardened or liquid, there are two different suggested					
ITED KINGDOM Bauder Ltd 70 Landseer Road, Ip	swich, Suffolk I	P3 0DH	Bauder reserves the right to update this data set without prior notice and			

UNITED KINGDOM Bauder Ltd 70 Landseer Road, Ipswich, Suffolk IP3 0D T: +44 (0)1473 257671 - E: <u>info@bauder.co.uk</u> www.bauder.co.uk Bauder reserves the right to update this data set without prior notice and this document is uncontrolled if printed or stored. Always confirm the latest version is used for the adoption of this product, available from our website: bauder.co.uk/technical-centre. Intended use of this product should be verified with Bauder to ensure suitability and compliance with applicable guidance, regulations, legislations, project requirements, specifications, and installation techniques.





#### waste codes:

Catalysed, hardened PMMA resins 17 02 03 - 'Plastic.

<sup>1</sup>Un-catalysed, liquid PMMA resins 08 01 11 – 'Waste paint and varnish containing organic solvents or other dangerous substances'.

Further information/ documents	Current documents such as brochures, installation guides, etc. can be found by visiting www.bauder.co.uk		
Certification and environmental information	BBA Certificate	14/5152	
	Environmental product Declaration	EPD-DBC-20190116-IBE1-EN	
International Standards Organisation (ISO)	ISO 9001:2015 Quality Management	Certificates EN1271 and DEKRA 80408283	
	ISO 14001:2015 Environmental Management	Certificates A10552 and DEKRA 170408038	

#### Installation Guidance

Installation is to be carried out by Bauder Approved Contractors in accordance with the specification and guidelines. Please consult the Bauder technical department.

#### Substrate assessment / pre-treatment / preparation

Ensure that the substrate is clean, dry, and free from dust, laitance, grease, oil and any other contamination, including surface applied curing membranes or treatments. The substrate must be assessed, treated, and prepared in accordance with the Bauder project specification.

## Initial mixing / decanting

Thoroughly mix the resin in the drum with a slow speed mixer until the resin achieves a uniform consistency. If required to decant, mix in the drum before decanting a measured weight into a suitable container.

#### Mixing

Measure the appropriate weight of catalyst for the weight of resin and the temperature as detailed in the table below and on the label on the back of the drum. Add the catalyst to the pre-mixed / decanted resin.

Thoroughly mix the resin and catalyst using a slow speed mixer for a minimum 2 minutes until the catalyst has been evenly distributed. Leave for a minimum of 1 minute to allow the catalyst to fully dissolve.

Re-mix and use the mixed material within the pot life.

Temperature	0°C to +5°C	+5°C to +15°C	+15°C to +35°C
Catalyst to resin %	6%	4%	2%
Catalyst per 10kg drum of resin	0.60kg	0.40kg	0.20kg

Note: Catalyst is supplied in 0.1 kg bags or 25 kg box.

#### Installation

For overbanding, apply catalysed LiquiPAVE R at a minimum rate of 1.5kg/m<sup>2</sup> using a synthetic deep pile roller. Roll a suitable width of Bauder 110g Reinforcement Fleece into the wet resin, pressing trapped air free using the roller, ensuring a minimum 50mm end lap. Ensure the Bauder 110g Reinforcement Fleece is always fully saturated before applying a further coat of LiquiPAVE R (1.0kg/m<sup>2</sup>) wet on wet.

For the LiquiPAVE RF application refer to the Bauder specification and the LiquiPAVE RF technical data sheet.

Note: Consumption rates are based on smooth, even, non-absorbent substrates.

#### Surfacing

Apply the Bauder Balcony, Walkway or Terrace surfacing option as detailed in the Bauder project specification.

#### Interruptions during works

Where work is interrupted for more than 12 hours or if soiled by rain etc., proceed as follows;

- For areas that are not fully aggregate filled, use Bauder PMMA Cleaner to clean and reactivate the transition area. Overlay after the Bauder PMMA Cleaner has
  evaporated and a minimum 20 minutes / maximum 60 minutes after application.
- For areas where the surface is aggregate filled, ensure that the surface is clean, dry, and free from dust, grease, oil and any other contaminants prior to overlay but do not apply Bauder PMMA Cleaner.

### **Tool cleaning**

Clean tools with Bauder PMMA Cleaner. Refer to the specific technical data sheet.

# Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as a substance/mixture; therefore, this product does have a requirement for a Safety Data Sheet.



UNITED KINGDOM Bauder Ltd 70 Landseer Road, Ipswich, Suffolk IP3 0DH T: +44 (0)1473 257671 - E: <u>info@bauder.co.uk</u> www.bauder.co.uk