

## Bauder 110g Reinforcement Fleece

05.12.2025

<b>Product description</b>	Polyester reinforcement fleece used in conjunction with Bauder LiquiTEC products to provide strength and allow elasticity of the membranes without splitting.
<b>Application fields</b>	Reinforcement in the Bauder LiquiTEC Roof, Detail and Balcony Systems. It is suitable for use in cold roof, warm roof, and inverted applications.



<b>Article Number</b>	GB81006010	Reinforcement Fleece 1050mm
	GB81006015	Reinforcement Fleece 150mm
	GB81006020	Reinforcement Fleece 262mm
	GB81006030	Reinforcement Fleece 350mm
	GB81006040	Reinforcement Fleece 525mm

Characteristic	Unit	Value
<b>Width</b>	mm	1050 525 350 262 150
<b>Length</b>	m	50
<b>Nett weight</b>		
1050	kg/roll	5.78
525		2.89
350		1.93
262		1.44
150	g/roll	825
<b>Colour</b>		White
<b>Weight</b>	g/m <sup>2</sup>	110
<b>Base</b>		Polyester
<b>Shelf life</b>		Unlimited
<b>Max. tensile force length</b>	N/50mm	> 200
<b>Max. tensile force transverse</b>	N/50mm	> 160
<b>Elongation at max. tensile force length</b>	%	> 50
<b>Elongation at max. tensile force transverse</b>	%	> 50

# Technical data sheet



## Storage guidance

Store on end in a dry place above freezing and protect from moisture. Store the materials outdoors, on end/upright and off the ground with suitable robust UV resistant, flame-retardant tarpaulin. Ensure the product(s) are clear of buildings and any other storage areas. Where there are storage containers on site, these may be suitable for storing products.

## Packaging material

The products are packaged in polyethylene bags.

Weight of packaging approximately	
1050	100g
525	60g
350	40g
262	30g
150	10g

## Handling/PPE

All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using the product, installers should be provided with, and wear, suitable personal protective equipment.

## Disposal guidance

Recommended EWC waste codes:

- Non contaminated fleece: 20 01 11 textiles.
- Fleece contaminated with resin (dried): 17 09 04 mixed construction and demolition wastes other than those mentioned in 17 09 01, 17 09 02 and 17 09 03.
- Fleece contaminated with resin (moist and will not dry): 17 09 03 other construction and demolition wastes (including mixed wastes) containing hazardous substances.

## Further information/ documents

Current documents such as brochures, installation guides, etc. can be found by visiting [www.bauder.co.uk](http://www.bauder.co.uk)

## International Standards Organisation (ISO)

ISO 9001:2015 Quality Management  
Certificates EN1271 and DEKRA 80408283

ISO 14001:2015 Environmental Management  
Certificates A10552 and DEKRA 170408038

## Installation Guidance

Installation is to be carried out by Bauder Approved Contractors in accordance with the specification and guidelines. Please consult the Bauder technical department.

Apply an even layer of embedment resin in accordance with the Bauder project specification and immediately embed the Bauder 110g Reinforcement Fleece into the wet resin, pressing trapped air free using the roller. Ensure the Bauder 110g Reinforcement Fleece is always fully saturated before applying a further layer of resin wet-on-wet in accordance with the specification.

Ensure a minimum 50mm overlap between adjacent sections (100mm if left over 12 hours).

**Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as an article; therefore this product does not have a requirement for a Safety Data Sheet.**

