

Bauder LiquiFINISH

V5 26.10.2023

Product description

LiquiFINISH is a fast curing cold applied liquid final coat for use with LiquiTEC systems. The product is a PMMA based resin and requires the addition of catalyst to trigger curing. It is solvent, isocyanate and halogen free.

Application fields


LiquiFINISH is used to seal and bind the quartz wearing course in LiquiTEC Balcony, Walkway & Terrace Systems, and to provide the desired colour to the finished waterproofing. It can also be used to provide a colour change to the LiquiTEC Roof system and as the seal coat to maintenance heavy duty walkways.

The product must be mixed with Bauder Catalyst to cure. Bauder Catalyst must be ordered separately.



Article Number

GB81002070 – Blue Grey RAL 7031 approx.
GB81002080 – Stone Grey RAL 7030 approx.
GB81002090 – Traffic Grey RAL 7043 approx.

Characteristic	Unit	Value
Gross weight	kg	11.1
Net weight	kg	10
Colour		<div style="display: flex; flex-direction: column; gap: 10px;"> <div style="display: flex; align-items: center;">  Blue grey (RAL 7031 approx.) </div> <div style="display: flex; align-items: center;">  Traffic grey (RAL 7043 approx.) </div> <div style="display: flex; align-items: center;">  Stone grey (RAL 7030 approx.) </div> </div>
Base		Poly methyl methacrylate
Coverage	kg/m ²	Varies – refer to Bauder specification
Shelf life unopened	months	6
Ambient and substrate temperature	°C	0 to +35 (Where the temperature falls outside of this, please refer to Summer & Winter advice documents from Bauder).
Atmospheric relative humidity	%	≤ 95
Dew point	°C	3° above dew point
Pot life	minutes	15 approx.
Curing time at 20°C*		
Rainproof	minutes	30 approx.
Overcoat / traffic time		60 approx.
Able to withstand stress		120 approx.
Reaction to fire	13501-1	Euroclass E

*Times will be slightly increased at lower temperatures and slightly reduced at higher temperatures.

Technical data sheet



Storage guidance	Store unopened in a cool, dry, well-ventilated place above freezing, out of direct sunlight and in the original container.	
Packaging material	The product is packaged in tin plate steel pails with a tin plate steel lid and ring latch. Weight of packaging approximately 1.1kg.	
Handling/PPE	All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using the product, installers should be provided with, and wear, suitable personal protective equipment.	
Emptying and disposal guidance	Containers which have been emptied, but not washed out in line with the specific methods and calculations prescribed in WP1 and WM3, should be classified as packaging containing residues of/or contaminated by hazardous substances using waste code 15-01-10. Containers with hazardous residues that have been emptied and washed-out in line with the method and calculations which are detailed in the industry guidance can be classified as non-hazardous waste packaging. Dependent upon the state of the waste resin, hardened or liquid, there are two different suggested waste codes: Catalysed, hardened PMMA resins 17 02 03 – 'Plastic. 'Un-catalysed, liquid PMMA resins 08 01 11 – 'Waste paint and varnish containing organic solvents or other dangerous substances'.	
Further information/ documents	Current documents such as brochures, installation guides, etc. can be found by visiting www.bauder.co.uk	
Certification and environmental information	BBA Certificate	14/5152
	Environmental product Declaration	EPD-DBC-20190116-IBE1-EN
International Standards Organisation (ISO)	ISO 9001:2015 Quality Management	Certificates EN1271 and DEKRA 80408283
	ISO 14001:2015 Environmental Management	Certificates A10552 and DEKRA 170408038

Installation Guidance

Installation is to be carried out by Bauder Approved Contractors in accordance with the specification and guidelines. Please consult the Bauder technical department.

Substrate assessment / pre-treatment / preparation

Ensure that the substrate is clean, dry, and free from dust, laitance, grease, oil, and any other contamination. The substrate must be assessed, treated, and prepared in accordance with the Bauder project specification.

Initial mixing / decanting

Thoroughly mix the resin in the drum with a slow speed mixer until the resin achieves a uniform consistency; If required to decant, mix in the drum before decanting a measured weight into a suitable container.

Mixing

Measure the appropriate weight of catalyst for the weight of resin and the temperature as detailed in the table below and on the label on the back of the drum. Add the catalyst to the pre-mixed / decanted resin.

Thoroughly mix the resin and catalyst using a slow speed mixer for a minimum 2 minutes until the catalyst has been evenly distributed. Leave for a minimum of 1 minute to allow the catalyst to fully dissolve.

Re-mix and use the mixed material within the pot life.

Temperature	0°C to +5°C	+5°C to +15°C	+15°C to +35°C
Catalyst to resin %	6%	4%	2%
Catalyst per 10kg drum of resin	0.60kg	0.40kg	0.20kg

Note: Catalyst is supplied in 0.1 kg bags or 25 kg box.

Installation

Apply by roller to the substrate. For full details refer to the Bauder project specification.

Application

Add catalyst to the LiquiFINISH at the rate indicated on the container and apply using a synthetic deep pile roller at the rates indicated below.

Aggregate Finish Coat: Apply LiquiFINISH at a minimum rate of 0.65kg/m².

Upstands, Details and Areas Without Aggregate: Apply LiquiFINISH at a minimum rate of 0.5kg/m².

For upstand details and sloping areas in excess of 250mm high, add 1-2% Liquid Thixo to the catalysed resin and stir thoroughly prior to application.

Technical data sheet



Interruptions during works

Where work is interrupted for more than 12 hours or if soiled by rain etc., proceed as follows:

- For areas that are not fully aggregate filled, use Bauder PMMA Cleaner to clean and reactivate the transition area. Overlay after the Bauder PMMA Cleaner has evaporated and a minimum 20 minutes / maximum 60 minutes after application.
- For areas where the surface is aggregate filled, ensure that the surface is clean, dry, and free from dust, grease, oil, and any other contaminants prior to overlay but do not apply Bauder PMMA Cleaner.

Tool cleaning

Clean tools with Bauder PMMA Cleaner. Refer to the specific technical data sheet.

Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as a substance/mixture; therefore, this product does have a requirement for a Safety Data Sheet.

