Technical data sheet



Bauder LiquiPASTE Mortar

V5 26.10.2023

LiquiPASTE Mortar is a fast curing cold applied liquid filler for horizontal and Product description

vertical repairs, to be used after the application of LiquiPRIME. The product is a PMMA based resin and requires the addition of catalyst to trigger curing. It is

solvent, isocyanate and halogen free.

Application fields LiquiPASTE Mortar is used as a fast curing substrate filler for larger indentations, recesses and holes. It is used with the LiquiTEC Roof, Detail and Balcony Systems. It consists of LiquiPASTE bulked out with Bauder Quartz.

The resin product must be mixed with Bauder Catalyst to cure. Bauder

Catalyst must be ordered separately.



Article Number GB81004010 (LiquiPASTE)

Characteristic	Unit	Value	
Gross weights	kg		
LiquiPASTE		16.1	
Bauder Quartz (0.7 – 1.2mm)		25.4	
Net weight			
LiquiPASTE Mortar comprises			
LiquiPASTE	kg	15 Drum	
Bauder Quartz (0.7 – 1.2mm)		25 bag	
Bauder Catalyst		0.1kg bag / 25kg box	
Mixing ratio			
LiquiPASTE		1 part (15kg)	
Bauder Quartz (0.7 – 1.2mm)		1 part (15kg)	
Bauder Catalyst		Varies- see mixing section	
Colour		Pebble Grey RAL 7032 (approx.)	
Base		Poly methyl methacrylate	
Weight/density	kg/mm/m²	2.00 approx.	
Shelf life unopened	months	6	
Ambient and substrate temperature	°C	0 to +35 (Where the temperature falls outside of this, please refer to Summer &	
		Winter Advice documents from Bauder).	
Atmospheric relative humidity	%	≤ 95	
Dew point	°C	3° above dew point	
Pot life	minutes	10 approx.	
Curing time at 20°C*			
Rainproof		30 approx.	
Overcoat / traffic time	minutes	60 approx.	
Able to withstand stress		120 approx.	
*Times will be slightly increased at lower temperatures	and slightly reduced at	higher temperatures.	

Storage guidance Store unopened in a cool, dry, well-ventilated place above freezing, out of direct sunlight and in the original

Packaging material The LiquiPASTE product is packaged in tin plate steel pails with a tin plate steel lid and ring latch.

Weight of packaging approximately 1.1kg.

Bauder Quartz is packaged in a polyethylene sack, weighing approximately 0.4kg.

Handling/PPE All persons using the product should be fully aware of the manual handling methods as roofing materials are

heavy and can cause serious injury. When using the product, installers should be provided with, and wear,

suitable personal protective equipment.

Technical data sheet



Emptying and disposal guidance

Containers which have been emptied, but not washed out in line

with the specific methods and calculations prescribed in WP1 and WM3, should be classified as packaging containing residues of/or contaminated by hazardous substances using waste code 15-01-10. Containers with hazardous residues that have been emptied and washed-out in line with the method and calculations which are detailed in the industry guidance can be classified as non-hazardous waste packaging.

Dependent upon the state of the waste resin, hardened or liquid, there are two different suggested

waste codes:

Catalysed, hardened PMMA resins 17 02 03 - 'Plastic.

'Un-catalysed, liquid PMMA resins 08 01 11 - 'Waste paint and varnish containing organic solvents or

other dangerous substances'.

www.bauder.co.uk

International Standards Organisation (ISO) ISO 9001:2015 Quality Management Certificates EN1271 and DEKRA 80408283

ISO 14001:2015 Environmental Management Certificates A10552 and DEKRA 170408038

Installation Guidance

Installation is to be carried out by Bauder Approved Contractors in accordance with the specification and guidelines. Please consult the Bauder technical department.

Substrate assessment / pre-treatment / preparation

Ensure that the substrate is clean, dry, and free from dust, laitance, grease, oil and any other contamination.

The substrate must be assessed, treated, and prepared in accordance with the Bauder project specification. Apply the relevant primer ensuring it is applied into the crack/recess and allow to cure before applying LiquiPASTE Mortar.

Initial mixing / decanting

Thoroughly mix the resin in the drum with a slow speed mixer until the resin achieves a uniform consistency;

If required to decant, mix in the drum before decanting a measured weight into a suitable container.

Mixing

Measure the appropriate weight of catalyst for the weight of resin and the temperature as detailed in the table below and on the label on the back of the drum. Add the catalyst to the pre-mixed / decanted resin.

Thoroughly mix the resin and catalyst using a slow speed mixer for a minimum 2 minutes until the catalyst has been evenly distributed. Leave for a minimum of 1 minute to allow the catalyst to fully dissolve.

Add the aggregate up to a maximum 1 part aggregate to 1 part resin (by weight) and mix with a slow speed mixer until the mixture achieves a uniform consistency; Re-mix and use the mixed material within the pot life.

Temperature	0°C to +25°C	+25°C to +35°C
Catalyst to resin %	6%	4%
Catalyst per 15kg drum of resin	0.90kg	0.60kg

Note: Catalyst is supplied in 0.1 kg bags or 25 kg box.

Installation

Apply by trowel or spatula to the substrate. For full details refer to the Bauder project specification.

Application: Coverage will depend on the void being filled.

Interruptions during works

Where work is interrupted for more than 12 hours or if soiled by rain etc., proceed as follows;

- For areas that are not fully aggregate filled, use Bauder PMMA Cleaner to clean and reactivate the transition area. Overlay after the Bauder PMMA Cleaner has evaporated and a minimum 20 minutes / maximum 60 minutes after application.
- For areas where the surface is aggregate filled, ensure that the surface is clean, dry, and free from dust, grease, oil, and any other contaminants prior to overlay but do not apply Bauder PMMA Cleaner.

Tool cleaning

Clean tools with Bauder PMMA Cleaner. Refer to the specific technical data sheet.

Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as a substance/mixture; therefore, this product does have a requirement for a Safety Data Sheet.