

PRODUCT DATA SHEET

Bauder K5K Capping Sheet

A top quality, heavy duty, torch-applied SBS elastomeric bitumen capping sheet. The product features a spunbond polyester reinforcement to allow the finished product to cope with structural movement without fracture, and a mineral finish to provide protection against UV degradation. The product is available in a choice of three colours – Charcoal Grey, Brown & Natural Slate.



SURFACE FINISHES

Top:	Mineral chippings*
Bottom:	Thermofusible polyethylene

PRODUCT INFORMATION AND TECHNICAL PERFORMANCE

Characteristic	Test method	Unit	Value	
Width		m	1	
Length		m	5	
Thickness		mm	5.2	
Weight	Brown/Natural Slate	kg/m ²	6	
	Charcoal Grey		6.5	
Reinforcement		g/m ²	250 – Spunbond polyester	
Cold bending test	EN 1109	°C	-36	
Softening point	EN 1110	°C	≥ + 120	
Tensile properties: max. tensile force	EN 12311-1	N/mm	Length: ≥ 1000 /50 (±10%)	Transverse: ≥ 1000/50 (±10%)
Tensile properties: elongation	EN 12311-1		%	Length: ≥ 45 (±5)
Watertightness	EN 1928		Type B - Passed	
Reaction to fire	EN 13501-1		Class E	

UNITED KINGDOM

Bauder Ltd
70 Landseer Road, Ipswich, Suffolk IP3 0DH
T: +44 (0)1473 257671 E: info@bauder.co.uk
bauder.co.uk

IRELAND

Bauder Ltd
O'Duffy Centre, Carrickmacross, Co. Monaghan
T: +353 (0)42 9692 333 E: info@bauder.ie
bauder.ie

PRODUCT DATA SHEET

CERTIFICATION AND ENVIRONMENTAL INFORMATION	
BBA Certificate	10/4744
Environmental Product Declaration	S-P-00414
International Standards Organisation (ISO)	ISO 9001:2015 Quality Management Certificates EN1271 (UK) and 70499/03-15_e (Germany) ISO 14001:2015 Environmental Management Certificates A10552 (UK) and 70499/03-15_d (Germany) ISO 50001: 2011 Energy Management Certificate 70499/03-15_c (Germany)
BRE Green Guide generic bituminous system rating	A+ to B dependant upon deck type

INSTALLATION GUIDANCE
Refer to the Bauder Installation Manual for guidance

*The mineral slate surface finish is a natural rock, also containing slate, basalt, sand and other constituent parts. With this being a mixture of natural and man-made products, the raw material may differ in colour and shade, over which we have no control. There may also be colour variations between each roll of membrane. Over time the colour of the membranes could change due to weather and environmental influences.

Bauder reserves the right to amend information and product specifications without prior notice. All reasonable care has been taken to ensure that all data is current at the time of print, however because Bauder pursues a policy of constant development we recommend ensuring that your copy of this information is current by contacting our Technical Department at technical@bauder.co.uk

Recommendations for use should be verified as to the suitability and compliance with actual requirements, specifications, installation techniques and any applicable laws and regulations.

UNITED KINGDOM

Bauder Ltd

70 Landseer Road, Ipswich, Suffolk IP3 0DH

T: +44 (0)1473 257671 E: info@bauder.co.ukbauder.co.uk**IRELAND**

Bauder Ltd

O'Duffy Centre, Carrickmacross, Co. Monaghan

T: +353 (0)42 9692 333 E: info@bauder.iebauder.ie