Technical data sheet

Joint width

Joint depth

Bauder Sealant

Product description

Application fields

Article Number

Joint size suitability

Bauder reserves the right to update this data set without prior notice and this document is uncontrolled if printed or stored. Always confirm the latest version is used for the adoption of this product, available from our website: bauder.co.uk/technical-centre. Intended use of this product should be verified with Bauder to ensure suitability and complicate with applicable suitable regioned and the product applications of the product the store of the product should be the suitable product and the suitability and complicate with applicable suitable suitability and complicate the suitable suitable suitability and complicate the suitable suitable suitability and complicate the suitable suitable suitability and complicate the suitability and complicat compliance with applicable guidance, regulations, legislations, project requirements, specifications, and installation techniques.

		20 maximum
Width: depth ratio (w above min/max restrictions)	ithin	2:1
Storage life	months	12
Typical Shore Hardness		50
Application temperature	°C	+5 to +35
Service temperature	°C	-40 to +120
Skin time @20°C/65%RH	mins	15
Chemical resistance		Resistant to most dilute acids and alkalis; organic solvents may cau sealant to swell and lose adhesion, Strong cleaning agents can cau deterioration and may affect the efficiency of the material.
UV resistance		Very good
Service life	years	20
Movement accommodation	%	Butt joints 70 (movement in tension and compression) Lap joints 125 (movement in shear)
Colour		Grey (Approx. RAL 7045)
Modulus at 100% extension	N/mm²	1.12
Ultimate elongation	%	220
Tensile strength at break	N/mm²	1.85

Bauder Sealant is a one-part high modulus modified polymer sealant,

6 – minimum

20 - maximum

25 - maximum (single application)

35 - maximum (multiple applications) 10 - minimum, porous substrates

6 - minimum, non-porous substrates

rubber. To be used in conjunction with Bauder Sealant Primer.

stone where counterflashings have been installed to protect the

waterproofing upstand.


GB60220105 (Sealant Kit) GB60220120 (Sealant Primer)

mm

mm

Service temperature	-U	-40 to +120	
Skin time @20°C/65%RH	mins	15	
Chemical resistance		Resistant to most dilute acids and alkalis; organic solvents may cause the sealant to swell and lose adhesion, Strong cleaning agents can cause deterioration and may affect the efficiency of the material.	
UV resistance		Very good	
Service life	years	20	
Movement accommodation	%	Butt joints 70 (movement in tension and compression) Lap joints 125 (movement in shear)	
Colour		Grey (Approx. RAL 7045)	
Modulus at 100% extension	N/mm²	1.12	
Ultimate elongation	%	220	
Tensile strength at break	N/mm²	1.85	
PRODUCT INFORMATION – Sealant Kit			
Primer	Bauder Sealant Primer = 500ml tin (yield approx. 125 metres per tin)		
Equipment	Polyethylene nozzles – caulking gun (not included)		
Quantity estimator (Joint size = metres per litre)	6 x 6 = 27.75 9 x 6 = 18.50 12 x 9 = 9.25 18 x 10 = 5.5 25 x 10 = 4.0		





BAUDE

making roofs secure.

UNITED KINGDOM Bauder Ltd 70 Landseer Road, Ipswich, Suffolk IP3 0DH T: +44 (0)1473 257671 - E: <u>info@bauder.co.uk</u> ler co uk

Technical data sheet



Storage guidance	The product must be stored in original unopened packaging in a cool, dry place out of direct sunlight, and must not be exposed to temperatures exceeding 35°C.	
Packaging material	Supplied in kit form in a cardboard box (readily recyclable) as follows – 25 x 380ml polyethylene cartridges Bauder Sealant. Polyethylene nozzles. 1 x 500ml tin Sealant Primer. Note: Packages will not be split.	
Handling/PPE	All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using the product, installers should be provided with, and wear, suitable personal protective equipment. No particular health hazards are associated with this product but please consult the relevant Safety Data Sheet for full information.	
Disposal guidance	Containers which have been emptied, but not washed out in line with the specific methods and calculations prescribed in WP1 and WM3, should be classified as packaging containing residues of/or contaminated by hazardous substances using waste code 15-01-10. Containers with hazardous residues that have been emptied and washed-out in line with the method and calculations which are detailed in the industry guidance can be classified as non-hazardous waste packaging.	
Further information/ documents	Current documents such as brochures, installation guides, etc. can be found by visiting <u>www.bauder.co.uk</u>	
International Standards Organisation (ISO)	ISO 9001:2015 Quality Management Certificate No. FM 01580	
	ISO 14001:2015 Environmental Management	

Certificate No. EMS 578299

Installation Guidance: Refer to the Bauder Installation Guide and project specification for guidance.

- Joint preparation The joint surfaces must be clean, dry and free from all contamination. The surfaces must be cleaned and primed with Bauder Sealant Primer.
- Joint Backing Where applicable, appropriate joint filler e.g. closed cell polyethylene foam, should be used to provide the correct joint depth.
- Application Bauder Sealant is supplied in cartridges. All joint preparation, priming and sealant application should be carried out in accordance with BS8000
 Part 16, the British Standard for the sealing of joints in buildings using sealants.
- Important: The information in this document is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control.

Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as a substance/mixture; therefore, this product does have a requirement for a Safety Data Sheet.

UNITED KINGDOM Bauder Ltd 70 Landseer Road, Ipswich, Suffolk IP3 0DH T: +44 (0)1473 257671 - E: info@bauder.co.uk www.bauder.co.uk

Bauder reserves the right to update this data set without prior notice and this document is uncontrolled if printed or stored. Always confirm the latest version is used for the adoption of this product, available from our website: bauder.co.uk/technical-centre. Intended use of this product should be verified with Bauder to ensure suitability and compliance with applicable guidance, regulations, legislations, project requirements, specifications, and installation techniques.