## Technical data sheet Bauder K5K Roofing membrane



## V4 22/11/2022

Product description	spunbono structural	r bitumen torch-on capping sheet. The product features a polyester reinforcement to allow the finished product to cope with movement without fracture, and a mineral finish to provide against UV degradation.		
Application fields	Capping sheet in a flat roof system. Used in 'torch-safe' areas where a gas torch is not prohibited.			
Surface	top:	Grey slate mineral		
	bottom:	Thermofusible polyethylene		
Reinforcement type and weight	polyester fleece 250 g/m²			
Article number	1721 4000			

Characteristic	Test method	Unit	Value
Length	EN 1848-1	m	5
Width	EN 1848-1	m	1
Thickness	EN 1849-1	mm	5,2
Mass per unit area	-	kg/m²	6
Straightness	EN 1848-1	mm/10m	<20
Reaction to fire	EN 13501-1	Class	E
Watertightness	EN 1928	-	passed
Flexibility at low temperature top	EN 1109	°C	≤-36
Flexibility at low temperature bottom	EN 1109	°C	≤-36
Flow resistance at elevated temperature top	EN 1110	°C	≥120
Flow resistance at elevated temperature bottom	EN 1110	°C	≥120
Max. tensile force length	EN 12311-1	N/50mm	1000(±10%)
Max. tensile force transverse	EN 12311-1	N/50mm	1000(±10%)
Elongation at max. tensile force length	EN 12311-1	%	45(±5)
Elongation at max. tensile force transverse	EN 12311-1	%	45(±5)
External fire performance	CEN/TS 1187	-	Product has been fire tested as part of a system assembly and this information can be obtained in the Fire Test Report available from Bauder Ltd.



Notified body: GPB, 1724 EN 13707, EN 13969



installation techniques.

Notified body: BBA 0836 BS EN 13707

## Technical data sheet Bauder K5K Roofing membrane



Product surface finish The mineral surface finish is a natural rock, also containing slate, basalt, sand and other constituent parts. With

this being a mixture of natural and man-made products, the raw material may differ in colour and shade, over which we have no control. There may also be colour variations between each roll of membrane for which the manufacturer assumes no liability. Over time the colour of the membranes could change due to weather and

environmental influences.

Product storage guidance On end/Upright - The membranes must also be protected from UV rays, moisture and heat.

Pallet size =24 rolls/120m² per pallet

Storage temperature range +5°C to +30°C

Packaging material The product will be delivered on wooden pallets with plastic overwrap to protect the product. Each roll has a

paper wrapping/tape to the external of the product, which must be removed before use.

Handling/PPE All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using/handling the product, installers should be provided with, and

wear, suitable personal protective equipment.

**Shelf life** When stored correctly, the product has no stated shelf life, however, for extended periods beyond 5 years, we

would suggest additional installation techniques may be required.

Disposal guidance Bitumen waste can be disposed of with household waste or commercial waste similar to household waste

(European waste catalogue EWC number 170302 "asphalt tar-free").

Re-use options of product Please refer to EPD stated below in Certification and environmental information.

visiting www.bauder.co.uk

10/4744

Certification and environmental BBA Certificate No.:

information

Environmental Product Declaration:

GlobalEPD-IntEPD S-P-00768

International Standards Organisation (ISO):

ISO 9001:2015 Quality Management

Certificates EN1271 (UK) and 70499/03-15\_e (Germany)

ISO 14001:2015 Environmental Management

Certificates A10552 (UK) and 70499/03-15\_d (Germany)

ISO 50001: 2011 Energy Management Certificate 70499/03-15\_c (Germany)

Safety Data Sheet Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures

in the EU & UK. This product is classed as an article; therefore, this product does not have a requirement for a

Safety Data Sheet.



Notified body: GPB, 1724 EN 13707, EN 13969



installation techniques.

Notified body: BBA 0836 BS EN 13707